

▲ APPLAUSE®

POWDER-FREE EXAMINATION GLOVES

OPAQUE
SYNTHETIC
NON-STERILE
AMBIDEXTROUS
SMOOTH
BEADED CUFF
FOR SINGLE USE ONLY
NON-LATEX

This 100% synthetic glove offers high elasticity and tensile strength. Durable, form-fitting and ideal for areas without aggressive chemicals. 510K approved for medical use.

- Synthetic material avoids the risk of latex protein allergies
- Smooth finish for a more natural feel





| PRODUCT CODE | | | | |
|--------------|------|--|--|--|
| S | Y201 | | | |
| М | Y202 | | | |
| L | Y203 | | | |
| XL | Y204 | | | |

| PACKAGING | | | | |
|-----------|------------|--|--|--|
| 100 | Gloves/Box | | | |
| 10 | Boxes/Case | | | |
| 10 | Boxes/Case | | | |

| GLOVE PROFILE | | ASTM D 5250 | Y20 |
|-----------------------|-----------------------------|----------------------|------------|
| Length | mm (inches) | min. 230 (9.1) | 240 (9.5) |
| Cuff Thickness | mm (mils) | n/a | 0.06 (2.4) |
| Palm Thickness | mm (mils) | min. 0.08 (3.1) | 0.08 (3.1) |
| Finger Thickness | mm (mils) | min. 0.05 (2.0) | 0.08 (3.1) |
| Tensile Strength | Before Aging After Aging | min. 11 min. 11 | 18 11 |
| Elasticity/Elongation | Before Aging After Aging | min. 300 min. 300 | 300 300 |
| Pinhole Defect Rate* | (AQL) | max. 2.5 | 1.5 |

^{*} Pinhole Defect Rate is FDA minimum requirement.











RECOMMENDED INDUSTRIES

